

02/16/00

3714 U.S. PTO

**UTILITY PATENT  
APPLICATION TRANSMITTAL**

(Only for new nonprovisional applications  
under 37 CFR 1.53(b))

Attorney Docket No.	<b>000155</b>	Total Pages	
First Named Inventor or Application Identifier			
<b>Masamichi HARADA</b>			
Express Mail Label No.			

Check Box, if applicable [ ] Duplicate

APPLICATION ELEMENTS FOR:  
**PROCESS FOR PRODUCING BARRIER FILM AND  
BARRIER FILM THUS PRODUCED**

ADDRESS TO: Assistant Commissioner for Patents  
BOX PATENT APPLICATIONS  
Washington, D.C. 20231

1. ☒ Fee Transmittal Form (Incorporated within this form)  
(Submit an original and a duplicate for fee processing)

2. ☒ Specification Total Pages [26]

3. ☒ Drawing(s) (35 USC 113) Total Sheets [8]

4. ☒ Oath or Declaration Total Pages [2]

a. ☒ Newly executed (original)

b. ☐ Copy from prior application (37 CFR 1.63(d))  
(for continuation/divisional with Box 17 completed).

i. ☐ Deletion of Inventor(s)  
Signed statement attached deleting inventor(s) named in prior application,  
see 37 CFR 1.63(d)(2) and 1.33(b).

5. ☐ Incorporation by reference (useable if box 4b is checked)  
The entire disclosure of the prior application, from which a copy of the oath or declaration is supplied under  
Box 4b, is considered as being part of the disclosure of the accompanying application and is hereby  
incorporated by reference therein.

6. ☐ Microfiche Computer Program (Appendix)

7. ☐ Nucleotide and/or Amino Acid Sequence Submission (if applicable, all necessary)

- a. ☐ Computer Readable Copy
- b. ☐ Paper Copy (identical to computer copy)
- c. ☐ Statement Verifying identity of above copies

**ACCOMPANYING APPLICATION PARTS**

8. ☒ Assignment Papers (cover sheet and document(s))

9. ☐ 37 CFR 3.73(b) Statement (when there is an assignee) ☒ Power of Attorney

JC564 U.S. PTO  
09/504923  
02/16/00

**UTILITY PATENT  
APPLICATION TRANSMITTAL**

(Only for new nonprovisional applications  
under 37 CFR 1.53(b))

Attorney Docket No. **000155**

First Named Inventor or Application Identifier

**Masamichi HARADA**

**PAGE 2 OF 3**

10. ☐ English translation Document (if applicable)

11. ☐ Information Disclosure Statement ☐ Copies of IDS Citations

12. ☒ Preliminary Amendment

13. ☒ Return Receipt Postcard (MPEP 503)

14. ☐ Small Entity Statement(s) ☐ Statement filed in prior application  
Status still proper and desired.

15. ☒ Claim for Convention Priority ☐ Certified copies of Priority Documents

a. Priority of \_\_\_\_\_ application no. \_\_\_\_\_ filed on \_\_\_\_\_ is claimed under 35 USC 119.

The certified copies/copy have/has been filed in prior application Serial No. \_\_\_\_\_.

(For Continuing Applications, if applicable).

16. ☐ Other \_\_\_\_\_

17. If a CONTINUING APPLICATION, check appropriate box and supply the requisite information:

☐ Continuation ☐ Division ☐ Continuation-in-part (CIP) of prior application no. \_\_\_\_/\_\_\_\_

FEE TRANSMITTAL	Number Filed	Number Extra	Rate	Basic Fee
The filing fee is calculated below				\$690.00
Total Claims	10 - 20		x \$18.00	
Independent Claims	4 - 3	1	x \$78.00	78.00
Multiple Dependent Claims			\$260.00	
Basic Filing Fee				768.00
Reduction by 1/2 for small entity				
Fee for recording enclosed Assignment			\$40.00	40.00
TOTAL				\$808.00

UTILITY PATENT  
APPLICATION TRANSMITTAL

(Only for new nonprovisional applications  
under 37 CFR 1.53(b))

Attorney Docket No.

000155

First Named Inventor or Application Identifier

Masamichi HARADA

PAGE 3 OF 3

[XX] A check in the amount of \$808.00 is enclosed to cover the filing fee of \$768.00 and the assignment recordation fee of \$40.00.

[ ] Please charge our Deposit Account No. 01-2340 in the total amount of \_\_\_\_\_ to cover the filing fee and the \_\_\_\_\_ assignment recordation fee. A duplicate of this sheet is attached.

[XX] The Commissioner is hereby authorized to charge payment for any additional filing fees required under 37 CFR 1.16 or credit any overpayment to Deposit Account No. 01-2340. A duplicate of this sheet is attached.

18. CORRESPONDENCE ADDRESS

ARMSTRONG, WESTERMAN, HATTORI  
McLELAND & NAUGHTON  
1725 K Street, N.W. Suite 1000  
Washington, D.C. 20006  
Telephone: (202) 659-2930  
Facsimile: (202) 887-0357

SUBMITTED BY

Typed or Printed Name Mel R. Quintos

Reg. No. 31,898

Signature *Mel R. Quintos*

Date: February 16, 2000

MRQ/yap

**IN THE UNITED STATES PATENT AND TRADEMARK OFFICE**

In re application of:

Masamichi HARADA

Serial Number: Not Yet Assigned

Group Art Unit: Unassigned

Filed: February 16, 2000

Examiner: Unassigned

For: PROCESS FOR PRODUCING BARRIER FILM AND BARRIER  
FILM THUS PRODUCED

**PRELIMINARY AMENDMENT**

Assistant Commissioner of Patents  
Washington, D.C. 20231

February 16, 2000

Sir:

Prior to the calculation of the filing fees of the above application, please amend  
the application as follows:

**IN THE ABSTRACT OF THE DISCLOSURE:**

Please delete the current Abstract of the Disclosure, in its entirety, and substitute  
in place therefor, the Abstract of the Disclosure attached herewith.

**IN THE SPECIFICATION:**

Please amend the specification, in its entirety, as follows:

- Page 1, line 5, before “relates” insert --generally--; and  
line 19, change “interconnectings” to --interconnections--.
- Page 2, line 4, change “To” to --In order to--;  
line 15, change “interconnectings” to --interconnections--;  
line 16, delete “a”;  
line 17, change “interconnectings” to --interconnections, --;  
line 19, after “films” insert --,--; and  
line 20, change “concretely speaking” to --specifically--.
- Page 3, line 1, change “By” to --In--; and  
line 19, change “troubles encountering” to --problems encountered--.
- Page 4, line 3, after “(W<sub>2</sub>N)” insert --,--; and  
line 12, change “To” to --In order to--.
- Page 5, line 11, delete “more”;  
line 13, after “more” (first occurrence) insert --,--;

line 20, after “more” (first occurrence) insert --,--; and

line 22, after “more” (first occurrence) insert --,--.

Page 6, line 3, after “more” insert --,--;

line 12, after “more” (first occurrence) insert --,--;

line 15, change “comprising” to --comprises--; and

line 20, after “gases” insert --;--.

Page 7, insert between lines 7 and 8 the following paragraph:

--These and other features of the invention will be understood upon reading of the following description along with the drawings.--; and

In each of lines 10, 12, 14, 16, 21 and 24, change “.” to --;--.

Page 8, line 2, change “.” to --; and--;

line 19, before “allow” insert --also--; and

line 20, delete “too”.

Page 9, line 14, delete “the” (first occurrence); and

line 19, after “large” insert --;--.

Page 10, line 1, change “be introduced each” to --each be introduced--;  
line 9, after “1” insert --,--;  
line 16, after “more” (first occurrence) insert --,--;  
line 21, after “more” (first occurrence) insert --,--;  
line 22, after “gas” insert --,--; and  
line 24, after “more” (first occurrence) insert --,--.

Page 12, line 14, after “compound” insert --,--; and  
line 15, after “silicide” insert --,--.

Page 13, line 4, after “Pa” insert --,--; after “preferably” insert --,--; and after  
“more” (first occurrence), insert --,--; and  
line 8, after “chart” insert --,--.

Page 14, line 2, after “room” insert --,--;  
line 4, after “opened” insert --,--; and after “then” insert --,--; and  
line 12, after “300°C” insert --,--.

Page 16, line 4, after “(3)” insert --,--; after “thus” insert --,--; and after  
“deposited” change “.” to --:--; and  
line 7, change “That is to say” to --In other words”.

Page 17, line 5, after “gas” insert --;--; and  
line 18, after “copper” insert --,--.

Page 18, line 5, after “Then” insert --,--;  
line 13, change “a” to --an--;  
line 20, change “laminated alternately” to --alternately laminated;--;

and

line 25, after “Then” insert --,--.

Page 19, line 25, change “in its scope” to --, within its scope,--.

#### **IN THE CLAIMS:**

Please amend claims 1 - 10 as follows:

1. (Amended) A process for producing a barrier film [which comprises],  
comprising the steps of:

providing a substrate in a vacuum atmosphere;

introducing a feedstock gas having a high temperature-melting point metal in its  
structure and a reductive nitrogen-containing gas comprising a nitrogen atom into said vacuum  
atmosphere; and



forming a thin film of the nitride of said high temperature-melting point metal on said substrate[;],

wherein a nitrogen-free auxiliary reductive gas is introduced into said vacuum atmosphere.

2. (Amended) The process for producing a barrier film according to claim 1, [which comprises a step of introducing] wherein said auxiliary reductive gas is introduced together with said feedstock gas and said reductive nitrogen-containing gas into said vacuum atmosphere.

3. (Amended) The process for producing a barrier film according to claim 2, [which comprises] wherein the introducing step includes a step of introducing said feedstock gas and said reductive nitrogen-containing gas into said vacuum atmosphere without introducing said auxiliary reductive gas.

Claim 4, line 4, change “;” to --,--; and  
line 8, change “but” to --, but--.

Claim 5, line 4, change “;” to --,--; and  
in each of lines 6 and 8, change “but” to --, but--.

Claim 6, line 4, change “;” to --,--; and  
line 6, change “but” to --, but--.

Claim 7, line 3, change “;” to --,--; and  
line 7, change “but” to --, but--.

8. (Amended) A process for producing a barrier film for forming a barrier film made of a thin film of the nitride of a high temperature-melting point metal on a substrate, [wherein;] comprising the steps of:

exposing the surface of said substrate [is exposed] to a plasma of hydrogen gas and a plasma containing at least one gas selected from [among] the group consisting of argon, nitrogen and helium gases[,]; and [then]

forming the thin film of the nitride of said high temperature-melting point metal [is formed] on the surface of the substrate.

Claim 9, line 2, delete “;”.

Claim 10, line 5, delete “;”.

#### **REMARKS**


The above amendments are believed to place the application in proper condition for examination. Early and favorable action is awaited.

In the event there are any additional fees required, please charge our Deposit

Account No. 01-2340.

Respectfully submitted,

ARMSTRONG, WESTERMAN, HATTORI,  
McLELAND & NAUGHTON



Mel R. Quintos  
Attorney for Applicant  
Reg. No. 31,898

Atty. Docket No. **000155**

Suite 1000  
1725 K Street, N.W.  
Washington, D.C. 20006  
Tel: (202) 659-2930  
Fax: (202) 887-0357

MRQ:lrj

Enclosure: Substitute Abstract of the Disclosure

## ABSTRACT OF THE DISCLOSURE

A thin nitride film having a low resistance is formed at a low film-forming temperature. In the step of forming a thin nitride film of a high temperature-melting point metal by introducing a feedstock gas having the high temperature-melting point metal and a reductive nitrogen-containing gas having a nitrogen atom into a vacuum atmosphere; an auxiliary reductive gas free from nitrogen is also introduced. The high temperature-melting point metal deposited due to the auxiliary reductive gas compensates for the deficiency of the high temperature-melting point metal of the deposited nitride; and thus enable the growth of the thin nitride film having a low resistance.

**PROCESS FOR PRODUCING BARRIER FILM AND  
BARRIER FILM THUS PRODUCED**

**FIELD OF THE INVENTION**

5           This invention relates to the technical field of metal interconnecting for semiconductor devices. More particularly, it relates to a process for producing a barrier film which is to be located between a copper interconnecting film and an insulation film, a barrier film which is to be located between  
10 a film containing Si, GaAs, etc. and a metal interconnecting for preventing silicidation, and a barrier film which is to be located between a highly dielectric film or a ferroelectric film and an electrode.



**BACKGROUND OF THE INVENTION**

15           In recent years, it has been required to more and more speed up the operations of semiconductor devices. To satisfy this requirement, studies have been undertaken on low-resistant copper interconnectings as a substitute for aluminum interconnectings.

20           However, copper occurs as an impurity in semiconductor crystals. In addition, it suffers from a problem of having a large diffusion coefficient in silicon crystals or silicon oxide. Therefore, it has been a practice that a thin film comprising the nitride of a high temperature-melting point  
25 metal (a thin tungsten nitride film, etc.) is formed as a barrier

film on the surface of a silicon substrate or a thin silicon oxide film and then a copper interconnecting film is formed on the surface of the barrier film.

To form such a barrier film, the sputtering method, the heat CVD method or the PE-CVD method is used. In the sputtering method, a high temperature-melting point metal is employed as a target. In the heat CVD method, a thin nitride film is formed by the following reduction reactions. Formula (1) shows a case wherein tungsten is used, while formula (2) shows another case wherein titanium is used.



In case of forming a semiconductor device with multi-layered interconnecting, it is needed to laminate copper interconnectings while inserting interlayer insulation films between them. In a semiconductor device to be operated at a high speed, the resistance of the copper interconnectings as well as the capacity of the interlayer insulation films and the resistance of the barrier films should be lowered so as to minimize signal transfer delay. More concretely speaking, a barrier film should have a resistance as low as 200 to 300  $\mu\Omega\text{cm}$ .

Although a thin nitride film having a low resistance can be formed by the sputtering method, only poor step coverage can be achieved thereby. Thus, no uniform barrier film can be formed in a viahole with a high aspect ratio by this method.

By the heat CVD method, on the other hand, a uniform barrier thin film can be formed in a viahole. However, the upper limit of the film-forming temperature in the heat CVD method resides in 400 to 500°C, since the dielectric constants of interlayer insulation films with low dielectric constants would be increased when exposed to a high temperature exceeding 500°C. At such a low film-forming temperature, the resistivity of, for example, a thin tungsten nitride film attains several thousand  $\mu\Omega\text{cm}$ , which makes it impossible to give barrier films with low resistance.

With respect to the CVD methods, barrier films with low resistance can be formed at a low temperature by the MOCVD method with the use of organometallic compounds or the plasma CVD method. However, the organometallic compounds are expensive, while the plasma CVD method has a problem of achieving only poor step coverage. Thus, these methods are not usable in practice.

#### SUMMARY OF THE INVENTION

The present invention, which has been made to overcome the above-described troubles encountering in the conventional art, aims at providing a barrier film having a value of low resistivity and good step coverage.

The present inventors analyzed thin films of high temperature-melting point metal nitrides formed by the conventional heat CVD method and, as a result, found that the high temperature-melting point metal atoms were provided only

in an insufficient amount. In the case of tungsten, for example, a tungsten nitride in the conventional art fails to establish the stoichiometric composition ( $W_2N$ ) but shows a composition  $W_xN$  wherein x ranges from about 1.5 to 1.6. It is assumed that

5 such insufficient supply of metal atoms in a nitride might worsen the crystallinity of the thin nitride film, thereby elevating the value of the resistance.

In the present invention which has been completed based on the above-described finding, attempts are made to

10 approximate the composition of the nitride of a high temperature-melting point metal closely to the stoichiometric level. To achieve this object, the present invention relates to a process for producing a barrier film which comprises the steps of providing a substrate in a vacuum atmosphere,

15 introducing a feedstock gas having a high temperature-melting point metal in its structure and a reductive nitrogen-containing gas having a nitrogen atom into said vacuum atmosphere, and forming a thin film of the nitride of said high temperature-melting point metal on said substrate, wherein a

20 nitrogen-free auxiliary reductive gas is introduced into said vacuum atmosphere.

The present invention relates to the process for producing a barrier film, which involves the step of introducing said auxiliary reductive gas together with said feedstock gas

25 and said nitrogen-containing gas into said vacuum atmosphere.



The present invention relates to the process for producing a barrier film, which involves the step of introducing said feedstock gas and said nitrogen-containing gas into said vacuum atmosphere without introducing said auxiliary reductive gas.

The present invention relates to the process for producing a barrier film, wherein, in the step of introducing said auxiliary reductive gas together with said reductive nitrogen-containing gas and said feedstock gas, said reductive nitrogen-containing gas is introduced at a flow rate once or more higher than the flow rate of said feedstock gas, and said auxiliary reductive gas is introduced at a flow rate once or more but not more than 10 times higher than the flow rate of said reductive nitrogen-containing gas.

The present invention relates to the process for producing a barrier film, wherein, in the step of introducing said auxiliary reductive gas together with said reductive nitrogen-containing gas and said feedstock gas, said reductive nitrogen-containing gas is introduced at a flow rate once or more but not more than 5 times higher than the flow rate of said feedstock gas, and said auxiliary reductive gas is introduced at a flow rate 2 times or more but not more than 10 times higher than the flow rate of said reductive nitrogen-containing gas.

The present invention relates to the process for producing a barrier film, wherein, in the step of introducing

said auxiliary reductive gas together with said reductive nitrogen-containing gas and said feedstock gas, said auxiliary reductive gas is introduced at a flow rate once or more but not more than 15 times higher than the flow rate of the feedstock gas having said high temperature-melting point metal.

The present invention relates to the process for producing a barrier film, wherein, in the step of growing the thin film of the nitride of said high temperature-melting point metal, a diluent gas not reacting with said high temperature-melting point metal and a gas having an oxygen atom in its chemical structure are introduced so that the pressure of said vacuum atmosphere is regulated to 1 Pa or more but not more than 100 Pa.

The present invention relates to a process for producing a barrier film which comprising the steps of forming a barrier film made of a thin nitride film of a high temperature-melting point metal on a substrate, wherein the surface of said substrate is exposed to a plasma of hydrogen and a plasma of at least one gas selected from among argon, nitrogen and helium gases and then the thin film of the nitride of said high temperature-melting point metal is formed on the surface of the substrate.

The invention relates to a barrier film having a thin film of the nitride of a high temperature-melting point metal, wherein said thin nitride film has a content of said high

temperature-melting point metal exceeding the stoichiometric composition ratio thereof.

The invention relates to a barrier film having a thin nitride film a high temperature-melting point metal formed on a substrate and aiming at preventing the diffusion of metals in a thin interconnecting film formed on said thin nitride film, wherein said thin nitride film is free from silicon.

#### BRIEF DESCRIPTION OF THE DRAWINGS

Figs. 1(a) to (e) show the first half of a flow chart illustrating the process of the present invention.

Figs. 2(f) to (h) show the second half of a flow chart illustrating the process of the present invention.

Figs. 3(i) to (j) show the latter half of a flow chart illustrating the process of the present invention.

Fig. 4 shows an example of a CVD apparatus by which the process of the present invention can be embodied.

Fig. 5 is a graph which shows relationships between the resistivity of a thin tungsten nitride film formed by the process of the present invention and the flow rates of the feedstock gas, the reductive nitrogen-containing gas and the auxiliary reductive gas.

Fig. 6 is a graph which shows a change in the elemental content of a thin tungsten nitride film formed by the process of the present invention depending on the  $\text{SiH}_4/\text{WF}_6$  flow rate.

Fig. 7 is a graph which shows the composition of tungsten

nitride formed by the process of the present invention in the depth direction.

Fig. 8 is a graph which shows the composition of tungsten nitride of the conventional art in the depth direction.

5 In these drawings, each numerical symbol has the following meaning:

20 : substrate

24,33 : thin nitride films (barrier films)

25 : thin metal film

10 27,35 : interconnecting films.

#### DETAILED DESCRIPTION OF THE INVENTION

In the present invention which has the above-described constitution, a feedstock gas having a high temperature-melting point metal atom and a reductive nitrogen-containing gas are introduced into a vacuum atmosphere and the feedstock gas is thus reduced by the reductive nitrogen-containing gas to deposit the nitride of the high temperature-melting point metal, wherein a nitrogen-free auxiliary reductive gas is also introduced into the vacuum atmosphere so as to allow the deposition of the high temperature-melting point metal too.

Further, a diluent gas and a gas having an oxygen atom in its structure (oxygen gas, etc.) are simultaneously introduced. As a result, it becomes possible to form a nitride film having improved barrier performance and further lowered resistivity, compared with a case where no oxygen atom-

containing gas is introduced.

When the nitride of the high temperature-melting point metal is deposited at a low temperature, the high temperature-melting point metal in the thin nitride film becomes  
5 deficient. However, the high temperature-melting point metal atoms deposited by the auxiliary reductive gas compensate for the deficiency. Thus, the obtained thin nitride film has a composition wherein the content of the high temperature-melting point metal exceeds the stoichiometric level thereof.

10 The amount of the deposited metal may be smaller than the amount of the deposited nitride. However, the auxiliary reductive gas should be introduced in a somewhat larger amount than the deposition level, since the auxiliary reductive gas is inferior in the reactivity to the reductive nitrogen-  
15 containing gas.

When the auxiliary reductive gas is introduced at an excessively high rate, on the other hand, the content of the high temperature-melting point metal becomes unnecessarily large and, as a result, the thin film exhibits properties close  
20 to the properties of the high temperature-melting point metal rather than those of the nitride. When an auxiliary reductive gas containing Si is employed, there arises a problem that the content of Si in the thin nitride film is increased. Therefore, the reductive nitrogen-containing gas, the auxiliary reductive  
25 gas, the diluent gas and the gas having an oxygen atom in its

structure should be introduced each at an adequate rate.

For example, ammonia gas (i.e., the reductive nitrogen-containing gas) is introduced at rates 1.0, 2.6 and 5.0 times higher than that of tungsten hexafluoride (i.e., the feedstock gas) and the ratio of silane gas (i.e., the auxiliary reductive gas) to the ammonia gas is varied.

Fig. 5 shows the results wherein the abscissa indicates the introduction rate of the silane gas expressed by referring the introduction rate of the ammonia gas as to 1 while the ordinate indicates the resistivity of the thin tungsten nitride film thus formed.

As this graph shows, it is preferable that the reductive nitrogen-containing gas is introduced at a rate amount once or more larger than the introduction rate of the feedstock gas, while the auxiliary reductive gas is introduced at a rate 2 times or more but not more than 10 times larger than the introduction rate of the reductive nitrogen-containing gas.

The practically available resistivity of a barrier film ranges from about 200 to 300  $\mu\Omega\cdot\text{cm}$ . Thus, it can be understood from this graph that the reductive nitrogen-containing gas is introduced preferably at a flow rate 1 time or more but not more than 5 times higher than the flow rate of the feedstock gas and the auxiliary reductive gas is introduced preferably at a flow rate 2 times or more but not more than 5 times higher than the flow rate of the reductive nitrogen-containing gas.

Fig. 6 shows the elemental content of each high temperature-melting point metal nitride at various ratios of the flow rate of the feedstock gas to the flow rate of the auxiliary reductive gas in the step of forming high temperature-melting point metal nitrides. In this case,  $WF_6$  is used as the feedstock gas and  $SiH_4$  is used as the auxiliary reductive gas. Oxygen gas is introduced at 1.5 sccm.

As this graph shows, the high temperature-melting point metal nitride (WN in this case) contains Si when the ratio  $SiH_4/WF_6$  attains 15 or more. This graph also shows that  $W_xN$  thin films are formed within the scope of the ratio  $SiH_4/WF_6$  of 1 to 15 time.

Fig. 7 shows the results of Auger spectrochemical analysis of a thin tungsten nitride film formed at a film forming temperature of 400°C wherein the sputtering time given in the abscissa indicates the depth from the surface. As this graph shows, much tungsten is contained therein (about 4.0 tungsten atoms per nitrogen atom), thereby indicating the effect of the introduction of the auxiliary reductive gas.

Since the barrier film is oxidized when it is taken out into the atmosphere, oxygen is observed on the film surface. Although silicon is seemingly contained in the film, the content thereof is less than the detection limit, i.e., a measurement error.

Thus, the resistivity can be lowered by using the high

temperature-melting point metal in the thin nitride film at a level exceeding the stoichiometric composition ratio thereof while sustaining the barrier performance.

In the CMP process, a thin nitride film should be adhered closely to the surface of a substrate. When the surface of the substrate is cleaned with a plasma of at least one gas selected from among argon, nitrogen and helium gases, the plasma and the plasma of hydrogen gas, and a plasma of mixed nitrogen, the thin nitride film formed on this surface would not peel off even under a load of 1 kg/cm<sup>2</sup>, thereby achieving an adhesiveness usable in the CMP process.

When the thin nitride film contains silicon, the silicon reacts with the high temperature-melting point metal (tungsten, etc.) at a high temperature to form a silicon compound such as tungsten silicide to thereby increase the resistivity. Since the thin nitride film of the present invention is free from silicon, no silicon compound is formed and thus the resistivity can be stabilized at a low level.

For comparison, Fig. 8 shows the results of Auger spectrochemical analysis of a thin tungsten nitride film formed by the CVD method of the conventional art at a film forming temperature of 400°C. This thin film contains about 1.7 tungsten atoms per nitrogen atom, i.e., showing a smaller tungsten content. It also shows a high resistivity of 1000  $\mu\Omega$ cm or more.



In the step of the formation of the thin nitride film of the high temperature-melting point metal, it is preferable to regulate the pressure to 1 Pa or more but not more than 10000 Pa, still preferably 1 Pa or more but not more than 100 Pa.

## DESCRIPTION OF THE EMBODIMENTS OF THE INVENTION

Now, embodiments of the present invention will be described by reference to the attached drawings.

Figs. 1(a) to (d) show a flow chart which shows an example of the embodiment of the present invention. In Fig. 1(a), the numerical symbol 20 shows a substrate to be treated. This substrate 20 has a semiconductor substrate 21 made of single silicon crystal on the surface of which a primary coat film 22 and an insulation film 23 made of silicon oxide are formed. The primary film 22 and the insulation film 23 are provided with a hole 31. The surface of semiconductor substrate 21 is exposed at a bottom 32 of the hole 31.

A barrier film is to be formed on the surface of this substrate 20.

In Fig. 4, the numerical symbol 50 shows a CVD apparatus whereby the present invention can be embodied. This CVD apparatus 50 has a vacuum chamber 51 which is connected to a transport room (not shown). The vacuum chamber 51 is provided with a substrate holder 53 in the bottom side and an electrode 55 in the top side.

When a barrier film is to be formed on the substrate 20

by using this CVD apparatus 50, the substrate 20 is first brought into the transport room and the transport room and the vacuum chamber 51 are evacuated. Next, a gate valve 52 between the vacuum chamber 51 and the transport room is opened and then the substrate 20 is brought into the CVD apparatus 50.

The substrate holder 53 is provided with a substrate elevator unit 54 with which the substrate brought into the vacuum chamber 51 is placed on the substrate holder 53. In Fig. 4, the substrate 20 is thus placed on the substrate holder 53.

Subsequently, the heater in the substrate holder 53 is switched on and thus the substrate 20 is heated to a temperature of not lower than 300°C but not higher than 400°C.

The vacuum chamber 51 is provided with a gas inlet system 57 through which argon gas and ammonia gas are introduced into the vacuum chamber 51 each at a prescribed flow rate. By applying a high-frequency voltage between the substrate holder 53 and the electrode 55, ionized nitrogen and hydrogen are liberated from the ammonia gas. In this step, the ionized argon gas serving as a diluent gas is mixed with the ionized nitrogen and hydrogen to give a plasma.

The insulation film 23 on the surface of the substrate 20 is faced closely to the electrode 55. As the plasma is formed, the surface of the insulation film 23 and the surface of the semiconductor substrate 21 at the bottom of the hole 31 are exposed to the plasma and the organic deposits are decomposed

(i.e., cleaning).

The cleaning is performed at an ammonia gas flow rate of 75 sccm, an argon gas flow rate of 240 sccm, under a pressure of 40 Pa and at a high-frequency electrical power of 100 W.


5 After cleaning for about 50 seconds, the application of the high-frequency voltage is stopped to thereby extinguish the plasma. Although argon (Ar) gas is used in this case, it can be substituted by nitrogen (N<sub>2</sub>) gas, helium (He) gas or a mixture thereof.

10 Next, the flow rates of the ammonia gas and the argon gas are changed and, at the same time, tungsten hexafluoride (WF<sub>6</sub>) gas, silane gas and oxygen gas are introduced into the vacuum chamber 51 through the gas inlet system 57 together with the ammonia gas and the argon gas.

15 Since the ammonia gas is superior in the reactivity to the silane gas, the tungsten hexafluoride serves as the feedstock gas and the ammonia gas serves as the reductive nitrogen-containing gas. Thus, the reaction of reducing the feedstock gas proceeds. Since the ammonia gas contains  
20 nitrogen, tungsten nitride is deposited on the surface of the insulation film 23 and on the surface of the semiconductor substrate 21 in the hole 31 due to the reduction reaction represented by the above formula (1).

Although the silane gas introduced into the vacuum  
25 chamber 51 also has reductive properties, it is inferior in

reactivity to the ammonia gas and, therefore, serves as the auxiliary reductive gas. Since the silane gas has no nitrogen atom, the feedstock gas is reduced thereby in accordance with the following formula (3) and thus metal tungsten is deposited.



When metal tungsten is deposited, it is incorporated into the thin tungsten nitride film under growing. That is to say, metal tungsten is supplied during the growth of the thin tungsten nitride film. When the thin tungsten nitride film grows at a low temperature, the deficiency of tungsten is thus compensated for and a barrier film (a thin tungsten nitride film) having a composition close to the stoichiometric composition or one having a high temperature-melting point metal content exceeding the stoichiometric level can be formed.

10                      The thin tungsten nitride film may grow under, for example, the following conditions; substrate temperature: 380°C; feedstock gas flow rate: 5 sccm; reductive nitrogen-containing gas flow rate: 13 sccm; auxiliary reductive gas flow rate: 39 sccm; argon gas flow rate: 240 sccm; oxygen gas introduction rate: 1.5 sccm; pressure: 40 Pa.

15                      When the feedstock gas is subjected to the reduction reaction by the reductive nitrogen-containing gas and the auxiliary reductive gas for a prescribed period of time, a thin tungsten nitride film is formed on the surface of insulation film 23 and on the surface of the semiconductor substrate 21,

as shown in Fig. 1(b)24.

Next, the supply of the reductive nitrogen-containing gas is ceased and the flow rate of the auxiliary reductive gas is increased. Thus, the feedstock gas is reduced by the auxiliary  
5 reductive gas and metal tungsten is deposited. In Fig. 1(c), the numerical symbol 25 shows a thin metal tungsten film growing on the surface of the thin nitride film 24.

The thin metal tungsten film may be formed under, for example, the following conditions; substrate temperature:  
10 380°C; feedstock gas flow rate: 20 sccm; auxiliary reductive gas flow rate: 5 sccm; diluent (argon) gas introduction rate: 240 sccm; pressure: 40 Pa.

Although the thin nitride film 24 has a favorable barrier performance against copper, it has a higher resistivity than  
15 that of the high temperature-melting point metal. On the other hand, the film of the high temperature-melting point metal (for example, thin metal tungsten film, etc.) has a poor barrier performance against copper but has a much lower resistivity than that of the thin nitride film 24.

20 When a thin nitride film 24 is formed as a barrier film and a thin high temperature-melting point metal film is laminated thereon as in the above-described case, the resistivity can be lowered while sustaining the favorable barrier performance against copper.

25 On the contrary, a thin nitride film may be formed on a

high temperature-melting point metal film or the thin nitride film may be formed as a single layer.

After allowing the thin tungsten film 25 to grow for 20 to 30 seconds under the above-described conditions, the substrate 20 is taken out from the CVD apparatus 50. Then a thin copper film is grown on the surface of the thin high temperature-melting point metal film 25 by the metal plating method, the sputtering method, etc. In Fig. 1(d), the numerical symbol 26 shows this thin copper film 26.

After the formation of the thin copper film 26, the surface is abraded by the CMP method to thereby eliminate the thin copper film 26, the thin nitride film 24 and the thin metal film 25 on the insulation film 23. Thus, an interconnecting film 27 made of the thin copper film 26 is formed in the hole 31. The thin nitride film 24 is located between the interconnecting film 27 and the semiconductor substrate 21 and between the interconnecting film 27 and the insulation film 23 so as to prevent copper from diffusion.

Next, primary films 41 and 43 and insulation films 42 and 44 are laminated alternately and the surface of the interconnecting film 27 is windowed to form a hole or a groove, as shown in Fig. 2(g). In Fig. 2(g), the numerical symbol 38 shows the groove or hole. The interconnecting film 27 is exposed on the bottom of this groove or hole 38.

Then the substrate 20 is brought into the CVD apparatus

50 and a thin nitride film (a thin tungsten nitride film) is formed under the same conditions as in forming the thin nitride film shown in Fig. 1(b).

The numerical symbol 33 in Fig. 2(h) shows the thus formed thin nitride film which covers the inner face of the groove or hole 38 and the surface of the insulation film 44 and the surface of the interconnecting film 27.

Subsequently, the thin copper film 34 is grown by the metal plating method or the sputtering method, as shown in Fig. 3(i). Thus, the groove or hole 38 is filled with the thin copper film 34.

Finally, the surface is abraded by the CMP method. Thus, an interconnecting film 35 is formed by the thin copper film 34 filled into the groove or hole 38, as shown in Fig. 3(j).

Since the barrier film 33 is located between the interconnecting film 35 and the insulation films 42 and 44, the diffusion of copper into the insulation films 42 and 44 can be prevented.

In the above-described case, a thin tungsten nitride film is formed by using tungsten as the high temperature-melting point metal, ammonia gas as the reductive nitrogen-containing gas and silane gas as the auxiliary reductive gas. Although tungsten hexafluoride is used as the feedstock gas in the above case, it is also possible to use  $W(CO)_6$  gas therefor.

Moreover, the present invention involves in its scope

cases where barrier films are produced by using high temperature-melting point metals other than tungsten and forming thin films of the nitrides thereof. When titanium (Ti) is used as the high temperature-melting point metal, titanium halide gases ( $\text{TiF}_4$ ,  $\text{TiCl}_4$ , etc.) are usable as the feedstock gas. When tantalum (Ta) is used as the high temperature-melting point metal, tantalum halide gases ( $\text{TaCl}_5$ , etc.) are usable as the feedstock gas. It is also possible to use halides of Mo or Nb as the feedstock gas.

As the reductive nitrogen-containing gas containing a nitrogen atom, use can be made of  $\text{N}_2\text{H}_4$  gas,  $\text{NF}_3$  gas,  $\text{N}_2\text{O}$  gas, etc. in addition to  $\text{NH}_3$  gas.

As the nitrogen-free auxiliary reductive gas, use can be made of  $\text{H}_2$  gas,  $\text{Si}_2\text{H}_6$  gas,  $\text{PH}_3$  gas,  $\text{B}_2\text{H}_6$  gas etc. in addition to  $\text{SiH}_4$  gas.

As the diluent gas, it is also possible to use argon gas, nitrogen gas, helium gas or a mixture of these gases.

The cleaning conditions as described above are given merely by way of example. Therefore, the cleaning may be performed under different conditions. For example, similar effects can be achieved by carrying out the cleaning for 60 seconds at an argon gas flow rate of 100 sccm, under a pressure of 1.0 Pa at a high-frequency electric power of 150W.

After completing the cleaning under such conditions, additional cleaning may be performed by adding ammonia gas to



the argon gas.

According to the present invention, a barrier film (a thin film of the nitride of a high temperature-melting point metal) having a low resistance can be formed by the CVD method at a temperature of 500°C or lower, in particular, from 350 to 450°C. Therefore, interlayer insulation films are not damaged thereby.

Furthermore, the thin nitride film is formed by the heat CVD method, which makes it possible to achieve good step coverage.

**WHAT IS CLAIMED IS:**

1. A process for producing a barrier film which comprises the steps of:

providing a substrate in a vacuum atmosphere;

5 introducing a feedstock gas having a high temperature-melting point metal in its structure and a reductive nitrogen-containing gas comprising a nitrogen atom into said vacuum atmosphere; and

10 forming a thin film of the nitride of said high temperature-melting point metal on said substrate;

wherein a nitrogen-free auxiliary reductive gas is introduced into said vacuum atmosphere.

15 2. The process for producing a barrier film according to claim 1, which comprises a step of introducing said auxiliary reductive gas together with said feedstock gas and said reductive nitrogen-containing gas into said vacuum atmosphere.

20 3. The process for producing a barrier film according to claim 2, which comprises a step of introducing said feedstock gas and said reductive nitrogen-containing gas into said vacuum atmosphere without introducing said auxiliary reductive gas.

25 4. The process for producing a barrier film according to claim 2, wherein, in the step of introducing said auxiliary

reductive gas together with said reductive nitrogen-containing gas and said feedstock gas;

said reductive nitrogen-containing gas is introduced at a flow rate once or more higher than the flow rate of said feedstock gas, and said auxiliary reductive gas is introduced at a flow rate once or more but not more than 10 times higher than the flow rate of said reductive nitrogen-containing gas.

5. The process for producing a barrier film according to claim 1, wherein, in the step of introducing said auxiliary reductive gas together with said reductive nitrogen-containing gas and said feedstock gas;

said reductive nitrogen-containing gas is introduced at a flow rate once or more but not more than 5 times higher than the flow rate of said feedstock gas, and said auxiliary reductive gas is introduced at a flow rate 2 times or more but not more than 10 times higher than the flow rate of said reductive nitrogen-containing gas.

6. The process for producing a barrier film according to claim 2, wherein, in the step of introducing said auxiliary reductive gas together with said reductive nitrogen-containing gas and said feedstock gas;

said auxiliary reductive gas is introduced at a flow rate once or more but not more than 15 times higher than the flow

rate of the feedstock gas having said high temperature-melting point metal.

7. The process for producing a barrier film according to claim 1, wherein, in the step of growing the thin film of the nitride of said high temperature-melting point metal;

a diluent gas not reacting with said high temperature-melting point metal and a gas having an oxygen atom in its chemical structure are introduced so that the pressure of said vacuum atmosphere is regulated to 1 Pa or more but not more than 100 Pa.

8. A process for producing a barrier film for forming a barrier film made of a thin film of the nitride of a high temperature-melting point metal on a substrate, wherein;

the surface of said substrate is exposed to a plasma of hydrogen gas and a plasma containing at least one gas selected from among argon, nitrogen and helium gases, and then the thin film of the nitride of said high temperature-melting point metal is formed on the surface of the substrate.

9. A barrier film comprising a thin nitride film of a high temperature-melting point metal, wherein;

said thin nitride film has a content of said high temperature-melting point metal exceeding the stoichiometric

composition ratio thereof.

10. A barrier film comprising a thin nitride film of a  
high temperature-melting point metal formed on a substrate and  
5 aiming at preventing the diffusion of metals in an  
interconnecting thin film formed on said thin nitride film,  
wherein;

said thin nitride film is free from silicon.

# **ABSTRACT**

A thin nitride film having a low resistance is formed at a low film-forming temperature.

In the step of forming a thin nitride film 24 of a high temperature-melting point metal by introducing a feedstock gas having the high temperature-melting point metal and a reductive nitrogen-containing gas having a nitrogen atom into a vacuum atmosphere, an auxiliary reductive gas free from nitrogen is also introduced. The high temperature-melting point metal deposited due to the auxiliary reductive gas compensates for the deficiency of the high temperature-melting point metal of the deposited nitride and thus enable the growth of the thin nitride film 24 having a low resistance.








Fig.2 (f)




Fig.2 (g)




Fig.2 (h)






Fig.3 (i)




Fig.3 (j)




Fig.4




Fig.5




Fig.6




Fig.7





Fig.8 Prior Art



## Declaration for U.S. Patent Application

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention **entitled**  
PROCESS FOR PRODUCING BARRIER FILM AND BARRIER FILM THUS PRODUCED  
the specification of which is attached hereto unless the following is checked



was filed on \_\_\_\_\_ as United States Application Number or PCT International  
Application Number \_\_\_\_\_ and was amended on \_\_\_\_\_ (if applicable).

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claim(s), as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, § 1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, § 119 (a)-(d) of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application for which priority is claimed:

(List Prior  
foreign  
applications.

Priority Claimed

<u>Hei 11-38041</u> (Number)	<u>Japan</u> (Country)	<u>17/2/1999</u> (Day/Month/Year Filed)	<u>X</u> Yes <u>  </u> No
<u>Hei 11-192026</u> (Number)	<u>Japan</u> (Country)	<u>6/7/1999</u> (Day/Month/Year Filed)	<u>X</u> Yes <u>  </u> No
<u>                    </u> (Number)	<u>                    </u> (Country)	<u>                    </u> (Day/Month/Year Filed)	<u>  </u> Yes <u>  </u> No
<u>                    </u> (Number)	<u>                    </u> (Country)	<u>                    </u> (Day/Month/Year Filed)	<u>  </u> Yes <u>  </u> No

\_\_\_\_ See attached list for additional prior foreign applications

I hereby claim the benefit under Title 35, United States Code, § 120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, § 112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, § 1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application.

(List Prior U.S.  
Applications)

<u>                    </u> (Appln. Serial Number)	<u>                    </u> (Filing Date)	<u>                    </u> (Status: Patented, Pending, Abandoned)
<u>                    </u> (Appln. Serial Number)	<u>                    </u> (Filing Date)	<u>                    </u> (Status: Patented, Pending, Abandoned)
<u>                    </u> (Appln. Serial Number)	<u>                    </u> (Filing Date)	<u>                    </u> (Status: Patented, Pending, Abandoned)

I hereby appoint the following attorneys and/or agents to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

James E. Armstrong, III, Reg. No. 18,366, William F. Westerman, Reg. No. 29,988; Ken-Ichi Hattori, Reg. No. 32,861, Le-Nhung McLeland, Reg. No. 31,541; Ronald F. Naughton, Reg. No. 24,616, William G. Kratz, Jr., Reg. No. 22,631; Mel R. Quintos, Reg. No. 31,898; James P. Welch, Reg. No. 17,379; John R. Pegan, Reg. No. 18,069; Donald W. Hanson, Reg. No. 27,133; Stephen G. Adrian, Reg. No. 32,878; William L. Brooks, Reg. No. 34,129; John F. Carney, Reg. No. 20,276; Edward F. Welsh, Reg. No. 22,455; Patrick D. Muir, Reg. No. 37,403; Gay A. Spahn, Reg. No. 34,978; John P. Kong, Reg. No. 40,054; and Luke A. Kilyk, Reg. No. 33,251, Leonard D. Bowersox, Reg. No. 33,226.

Please direct all communications to the following address:

**ARMSTRONG, WESTERMAN, HATTORI,  
McLELAND & NAUGHTON**  
1725 K Street, N.W., Suite 1000  
Washington, D.C. 20006  
Telephone (202)659-2930 Fax:(202)887-0357

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Title 18 of the United States Code, § 1001 and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full name of sole inventor (given name, family name) MASAMICHI HARADA

Inventor's signature Masamichi Harada Date January 31, 2000

Residence c/o NIHON SHIMKU GIJUSTU KABUSHIKI KAISHA 2500, Hagisono  
Chigasaki-shi Kanagawa 253-8543 Japan Citizenship Japanese

Post Office Address same as the above

Full name of second inventor (given name, family name) \_\_\_\_\_

Inventor's signature \_\_\_\_\_ Date \_\_\_\_\_

Residence \_\_\_\_\_ Citizenship Japanese

Post Office Address same as the above

Full name of third inventor (given name, family name) \_\_\_\_\_

Inventor's signature \_\_\_\_\_ Date \_\_\_\_\_

Residence \_\_\_\_\_ Citizenship Japanese

Post Office Address same as the above

Full name of forth inventor (given name, family name) \_\_\_\_\_

Inventor's signature \_\_\_\_\_ Date \_\_\_\_\_

Residence \_\_\_\_\_ Citizenship Japanese

Post Office Address \_\_\_\_\_

Full name of fifth inventor (given name, family name) \_\_\_\_\_

Inventor's signature \_\_\_\_\_ Date \_\_\_\_\_

Residence \_\_\_\_\_ Citizenship Japanese

Post Office Address \_\_\_\_\_